

93-260 Thinnest Chemical Resistant Synthetic Composite Disposable Glove



Tough chemical protection, unparalleled comfort

- Three layer design for superior protection against harsh chemicals
- The thinnest chemical resistant disposable glove for enhanced tactility and dexterity
- Extra soft material and ergonomic design for outstanding fit, feel and flexibility
- Lower acceptable pinhole rate (0.65 AQL) for reliable protection against hazardous substances
- Tested against both fentanyl and gastric acid (vomit) to simulate hazardous, real world overdose situations

Industries

- Aerospace
- Automotive
- Automotive Aftermarket
- Life SciencesChemical

Recommended For

- Inspection, selecting, checking parts
- Assembly and inspection of components
- Equipment repair and maintenance
- Production line support and maintenance
- General Purpose Auto Aftermarket
- Oil, fluids and filter change
- Blending, compounding solids and liquids
- Sample taking and processing
- Transferring liquids and solids
- Transferring liquids and solids between vessels and tanks and process equipment







93-260 **Thinnest Chemical Resistant Synthetic Composite Disposable Glove**

TECHNICAL DATA SHEET

PRODUCT INFORMATION

	93-260		
Material	Nitrile + Neoprene (Polychloroprene)		
Color	Green		
Glove Design	Chlorinated, Powder-Free, Textured Fingers		
Cuff	Beaded		
Manufacturing/QMS Audit Standards	ISO 9001:2008		
Regulatory/Standards Compliance	Category III, EAC TP TC 019:2011, EN ISO 374-1:2016, EN 420:2003 + A1:2009, EN ISO 374-5:2016, EN 374:2003, EN 374:2003, EN 388:2003, EN 388:2016, EN 421:2010, FDA21 CFR 177-2600, ISO 9001		
Packaging	50 gloves per dispenser 10 dispensers per case 500 gloves per case		
Storage	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition		
Country of Origin	Sri Lanka		
User Needs Segment	High Risk		
Available sizes	XS (5.5 - 6), S (6.5 - 7), M (7.5 - 8), L (8.5 - 9), XL (9.5 - 10), XXL (10.5 - 11)		
Sensitisers	 Zinc 2-mercaptobenzothiazole Zinc Dibutyldithiocarbamate (ZDBC) Only a very small number of users may be sensitised to this ingredient in the glove and hence may develop irritant and/or allergic contact reactions. 		

PHYSICAL PROPERTIES

	Typical Values		Testing Method
Length (mm/inches)	285 / 11.22		ASTM D3767,EN420
Freedom from Holes (Inspection level I)	0.65 AQL		ASTM D5151,EN 455-1
Palm Thickness (mm/inches)	0.198 / 7.9		ASTM D3767,EN420
Finger Thickness (mm/inches)	ger Thickness (mm/inches) 0.20 / 7.		ASTM D3767,EN420
	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength (MPa)	≥ 22	≥ 26	ASTM D412 & D573
Elongation at Break (%)	≥ 620	≥ 520	ASTM D412
Force at break (N)	≥ 16	≥ 17	EN 455-2

Performance Standards and Regulatory Compliance



For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV Riverside Business Park Blvd International, 55 1070 Brussels, Belgium T: ± 32 (0) 2 528 74 00 F: ± 32 (0) 2 528 74 01

Asia Pacific Region

Asia Pacific Region Ansell Global Trading Center (Malaysia) Sdn Bhd Prima 6, Prima Avenue Block 3512, Jalan Teknokrat 6 63000 Cyberjaya Selangor, Malaysia T: +603 8310 6688 F: +603 8310 6699

North America Region

Ansell Healthcare Products LLC 111 Wood Avenue South, Suite 210 Iselin, NJ 08830, USA T: +1 800 800 0444 F: +1 800 800 0445 Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V. Blvd. Bernardo Quintana No. 7001-C, Biva. Bernardo Guintana No. /C G7001 Torre II. Suites 1304, 1305 y 1306. Col. Centro Sur, c.p. 76079 Gueretaro, Gro. Mexico T: +52 442 248 1544 / 248 3133

Australia

Ansell Limited Level 3,678 Victoria Street, Richmond, Vic, 3121 Australia T: +61 1800 337 041 F: +61 1800 803 578

Russia

Russia Ahcenn PYC 123610 Poccnr, Mockba Kpachonpechehckar Ha6. 12, n.3, op. 1304A Ten. +7 495 258 13 16









Ansell, [®] and [™] are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking [©] 2019 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

