

MidKnight[®] MK-296 Distinctive, Black Nitrile Exam Glove



Distinct black color to mask stains

- Distinctive black color hides stains and provides contrast for improved visibility
- Fully textured design for confident grip
- Non-foaming for easy handling of objects in wet environments
- Tested against both fentanyl and gastric acid (vomit) to simulate hazardous, real world overdose situations



Industries

- Automotive
- Automotive Aftermarket
- Life Sciences
- Machinery and Equipment
- Healthcare

Recommended For

- Inspection, selecting, checking parts
- General Purpose Auto Aftermarket
- Use of cleaning tools and robotic equipment
- Oil, fluids and filter change
- Engine transmission and repair
- Tire rotation & changes
- Maintaining lab furniture and equipment
- Sample taking and processing
- Blending, compounding solids and liquids
- Raw material sample collection
- Weighing and dispensing of solid and liquid raw materials
- Inspection (picking, checking and marking)
- Standard, moderate risk examination procedures
- Protection from Type I latex allergy in HCW's or patients







MidKnight® MK-296 Distinctive, Black Nitrile Exam Glove

TECHNICAL DATA SHEET

PRODUCT INFORMATION

1 ROBOGI IIII ORI IATION				
	MidKnight® MK-296			
Material	Nitrile			
Color	Black			
Glove Design	Chlorinated, Powder-Free, Fully Textured			
Cuff	Beaded			
Manufacturing/QMS Audit Standards	ISO 13485:2003			
Regulatory/Standards Compliance	ASTM D6319, EN 420:2003 + A1:2009, FDA21 CFR 177-2600, US QSR/FDA 510(k) Medical Examination Grade			
Packaging	100 gloves per dispenser 10 dispensers per case 1000 gloves per case Also available in retail packs 10 gloves per pack 50 packs per carton/case			
Storage	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition			
Country of Origin	Malaysia			
User Needs Segment	Robust			
Available sizes	XS (5.5 - 6), S (6.5 - 7), M (7.5 - 8), L (8.5 - 9), XL (9.5 - 10), XXL (10.5 - 11)			

PHYSICAL PROPERTIES

	Typica	Typical Values	
Length (mm/inches)	245	245 / 9.6	
Freedom from Holes (Inspection level I)	1.5 /	AQL	ASTM D5151,EN 455-1
Palm Thickness (mm/inches)	0.12	0.12 / 4.7	
Finger Thickness (mm/inches)	0.14	0.14 / 5.5	
	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength (MPa)	≥ 27	≥ 24	ASTM D412 & D573
Elongation at Break (%)	≥ 500	≥ 400	ASTM D412
Force at break (N)	≥ 10	≥ 11	EN 455-2

For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV Riverside Business Park Blvd International, 55 1070 Brussels, Belgium T: +32 (0) 2 528 74 00 F: +32 (0) 2 528 74 01

Asia Pacific Region

Asia Pacific Region
Ansell Global Trading Center
(Malaysia) Sdn Bhd
Prima 6, Prima Avenue
Block 3512, Jalan Teknokrat 6
63000 Cyberjaya
Selangor, Malaysia
T: +603 8310 6688
F: +603 8310 6699

North America Region

Ansell Healthcare Products LLC 111 Wood Avenue South, Suite 210 Iselin, NJ 08830, USA T: +1 800 800 0444 F: +1 800 800 0445

Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V. Blvd. Bernardo Quintana No. 7001-C, BING. Bernardo Quintana No. 70 Q7001 Torre II. Suites 1304, 1305 y 1306. Col. Centro Sur, c.p. 76079 Queretaro, Qro. Mexico T: +52 442 248 1544 / 248 3133

Australia

Ansell Limited Level 3,678 Victoria Street, Richmond, Vic, 3121 Australia T: +61 1800 337 041 F: +61 1800 803 578

Russia

Alcenn PYC 123610 Poccnr, Mockba Kpachonpechehckar Ha6. 12, n.3, op. 1304A Ten. +7 495 258 13 16

Performance Standards and Regulatory Compliance



Ansell, $^{\odot}$ and $^{\odot}$ are trademarks owned by Ansell Limited or one of its affiliates, US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking $^{\odot}$ 2019 Ansell Limited. All Rights Reserved.

