



BEHR ULTRA®

INTERIOR SEMI-GLOSS ENAMEL PAINT



BEHR ULTRA Interior Semi-Gloss Enamel Paint sets a new standard for paint durability. BEHR ULTRA Interior Semi-Gloss is a 100% acrylic paint & primer^o with a stain-blocking formula featuring breakthrough innovation to deliver a beautiful finish that is truly durable enough for high-traffic areas. It provides advanced scuff & mar resistance, exceptional burnish resistance, easy stain removal, antimicrobial-mildew resistance, and hides in fewer coats.

Use on properly prepared, coated and uncoated, interior surfaces such as:

- Drywall/Gypsum Board
- Wood
- Other Non-Ferrous Metals
- Plaster
- Engineered Wood
- Architectural Plastics
- Concrete
- Steel
- Masonry
- Galvanized Steel
- Brick
- Aluminum
- Concrete Masonry Units
- Non-Ferrous Metals

TECHNICAL DATA

Tint Bases/Max Tint Load:

- No. 3750 Ultra Pure White 128 fl oz / 2 fl oz
- No. 3754 Medium Base 120 fl oz / 10 fl oz
- No. 3753 Deep Base 116 fl oz / 14 fl oz

Gloss: 45–55 @ 60°

Resin Type: 100% Acrylic

Weight per Gallon: 10.5 lb

% Solids by Volume: 38% ± 2%

% Solids by Weight: 51% ± 2%

VOC: < 50 g/L

Flash Point: N/A

Viscosity: 95–105 KU

Recommended Film Thickness:

- Wet: 6.4 mils / Dry: 2.4 mils @ 250 sq ft/gal
- Wet: 4.0 mils / Dry: 1.5 mils @ 400 sq ft/gal

Coverage: 250–400 sq ft/gal depending on application method and substrate porosity. Does not include the loss of material from spraying.

COMPLIANCE & CERTIFICATIONS

Complies with the below as of 12/1/2025

SCAQMD	YES	GREENGUARD** GOLD	YES
CARB SCM 2020	YES	LEED®+ v5	YES
CARB SCM 2007	YES	LEED®+ v4.1	YES
OTC PHASE II	YES	LEED®+ v4	YES
OTC	YES	WELL BUILDING STANDARD®	YES
LADCO	YES	NAHB/ICC NGBS	YES
EPA AIM	YES	CHPS®	YES
Environmental Product Declaration (EPD)	YES	MPI®	54
Health Product Declaration (HPD)	YES	MPI Extreme Green™ (X-Green)	54
DECLARE™ LBC Red List Free	YES		

Class A Fire Rating (Flame Spread Index: 0–25 & Smoke Development Index: 0–450) over non-combustible surfaces when tested in accordance with ASTM E84 Standard Test Method for Surface Burning Characteristics of Building Materials.

This coating conforms to USDA regulatory requirements for incidental food-contact materials intended for use on surfaces not in direct contact with food, such as walls, ceilings, and floors.

*GREENGUARD is a registered trademark of UL LLC.

†Please visit www.usgbc.org/LEED for additional details.

PERFORMANCE DATA

Scrubability (ASTM D2486; no shim):

Result: > 2,000

Flexibility (ASTM D522; method B):

Result: Pass

SPECIFICATIONS

Although BEHR ULTRA is a paint & primer (self-priming—first coat is the primer and the second coat is the finish) over most properly prepared surfaces, it is recommended for optimum performance to follow the primer recommendations provided below:

Drywall/Gypsum Wallboard:

Self-prime using 2 coats of BEHR ULTRA Interior Paint or

- 1 coat BEHR® Drywall Plus Interior Primer & Sealer No. 73
- 2 coats BEHR ULTRA Interior Paint

Masonry:

Self-prime using 2 coats of BEHR ULTRA Interior Paint or

- 1 coat BEHR Drywall Plus Interior Primer & Sealer No. 73
- 2 coats BEHR ULTRA Interior Paint

Plaster:

Self-prime using 2 coats of BEHR ULTRA Interior Paint or

- 1 coat BEHR Drywall Plus Interior Primer & Sealer No. 73
- 2 coats BEHR ULTRA Interior Paint

Wood:

Self-prime using 2 coats of BEHR ULTRA Interior Paint or

- 1 coat BEHR Drywall Plus Interior Primer & Sealer No. 73
- 2 coats BEHR ULTRA Interior Paint

Stain-Blocking:

Self-prime using 2 coats of BEHR ULTRA Interior Paint or

- 1 coat BEHR Kitchen, Bath & Trim Interior Stain-Blocking Primer & Sealer No. 75 or BEHR Multi-Surface Interior/Exterior Stain-Blocking Primer & Sealer No. 436
- 2 coats BEHR ULTRA Interior Paint

Ferrous and Non-Ferrous Metals:

- 1 coat BEHR Interior/Exterior Metal Primer No. 435 (recommended for optimal corrosion resistance or when priming over sound rusty metal surfaces) or BEHR Multi-Surface Interior/Exterior Stain-Blocking Primer & Sealer No. 436
- 2 coats BEHR ULTRA Interior Paint

NOTE: Certain substrate and exposure conditions, as well as project requirements, may necessitate the use of other substrate-specific or solution-driven primers. Please consult with a Behr Paint Company representative for specific primer recommendations.

When repainting involves a dramatic color change, a coat of primer will enhance the hiding performance of the topcoat.

APPLICATION

Brush: Nylon/polyester

Roller: ¾"–1½" nap roller cover, depending on surface texture

Airless Spray:

Tip: .015"–.019"

Filter: 60 mesh

Fluid Pressure: 1,400–2,400 psi

Thinning: Do not thin if using a roller or brush; however, if using a sprayer and thinning is required, thin with water at a rate of no more than 1/2 pint per gallon.

Dry Time: @ 77°F & 50% RH

To Touch: 1 hour

To Recoat: 2 hours

Full Cure: 4 weeks

Dry times are temperature, humidity, and film thickness dependent.

SURFACE PREPARATION

All surfaces must be clean, free of dust, chalk, oil, grease, wax, polish, mold and mildew stains, loose and peeling paint, rust and all other foreign substances.

Drywall: All drywall surfaces should be sufficiently sanded smooth. Remove any remaining drywall dust prior to priming. Allow all drywall compounds to be completely dry prior to coating.

Wood: Remove mill glaze with sandpaper to open the pores of the wood. For severe stains caused by mold, mildew, algae and fungus, apply a mildew stain removing product. Set nails and fill holes, scratches, and gouges with the appropriate patching material and let dry completely. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking and allow to dry completely. Patched and filled surfaces should be sanded smooth and dusted clean prior to coating.

Masonry: Allow to cure for 30 days. The pH must be 10 or lower prior to coating. Remove bond breakers and all form release and curing agents. Smooth masonry may require an adequate profile for adhesion. Remove all loose aggregate and debris. If painting cannot wait 30 days or pH level is above 10, allow the surface to cure 7 days and prime the surface with an alkali-resistant primer.

Plaster: New plaster should be thoroughly dried out and cured for a minimum of 30 days before painting. When cured, clean using a mixed solution of one part vinegar and one part water to remove efflorescence and neutralize. Prime the area with an alkali-resistant primer.

Steel: Minimum surface preparation is Hand Tool Cleaning in accordance with SSPC-SP2. Remove all oil and grease from the surface with a solvent in accordance with SSPC-SP1. For optimal performance, use Commercial Blast Cleaning in accordance with SSPC-SP6. Prime the area with a rust-inhibitive primer the same day as cleaned.

Galvanized Steel: Solvent clean new galvanized metal in accordance with SSPC-SP1 to remove oil and grease from the surface. Pre-treat with a phosphoric acid solution or a commercially-available etching solution. Galvanized

metal that has been passivated with chromates or silicates may require brush blasting in accordance with SSPC-SP16 to remove these treatments. Rusty galvanizing requires a minimum of Hand Tool Cleaning in accordance with SSPC-SP2. Prime the area the same day as cleaned.

Shop-Primed Steel: As there is potential for many forms of contamination during storage and transport, a thorough cleaning is always recommended for shop-primed surfaces. Paint exposed areas, i.e., where shop primer is abraded, with the same material as used for shop priming to comply with SSPC-PA 1 for touching up shop-primed surfaces. Note: Assess the integrity of the shop primer prior to application of subsequent coatings. Review all coatings intended for the project and confirm the compatibility between shop and field-applied coatings.

Aluminum: Remove all oil and grease from the surface with a solvent in accordance with SSPC-SP1. Prime the area the same day as cleaned.

Stain-Blocking: After priming, test for stain bleed-through by applying the topcoat to a small section. If the stain bleeds through the topcoat, apply a second coat of primer and test again before topcoating the entire area. If bleeding continues, primer may need a longer dry time before applying topcoat.

Previously Painted Surfaces: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate patching material and let dry completely. Remove all dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating.

Glossy Surfaces: For maximum adhesion, sand the surface thoroughly to provide a rough surface before coating.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. Contact Lead Information Center at 1-800-424-LEAD or log on to www.epa.gov/lead.

CLEAN-UP/DISPOSAL

Clean all tools and equipment with warm, soapy water. Do not dispose of this product down a drain. If spilled, contain material and remove with an inert absorbent. Dispose of contaminated absorbent, container and unused product in accordance with all current federal, state and local regulations. For recycling or disposal of empty containers, unused product and soiled rags, contact your household refuse collection service.

CAUTIONS/LIMITATIONS

- Protect from freezing.
- Do not use on floors.
- For best results, apply when air, material and surface temperatures are between 50°F and 90°F. Temperatures above 90°F can cause the paint to dry too fast, whereas temperatures below 50°F can inhibit proper film formation.
- Allow four weeks before washing or cleaning for full cure.
- Shelf life under normal conditions is two years unopened.

HEALTH & SAFETY INFORMATION

WARNING! CAUSES EYE AND SKIN IRRITATION. MAY CAUSE RESPIRATORY TRACT IRRITATION. Avoid contact with skin and eyes and avoid breathing vapors, spray mist and sanding dust. Sanding, grinding or abrading may release sanding dust, which may be harmful if inhaled and has been shown to cause lung damage or cancer with long term exposure. Do not breathe dusts, vapor, or spray mist. To avoid breathing in dust, vapors, and spray mist, open windows and doors or use other means to ensure fresh air entry during application, drying, sanding, and/or abrading. If properly used, a respirator (NIOSH approved with particulate pre-filter) may offer additional protection and should be used if adequate ventilation cannot be provided; obtain professional advice before using. If you experience eye watering, headaches, or dizziness during application or drying, increase fresh air or leave the area. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use.

FIRST AID: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 20 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

KEEP OUT OF REACH OF CHILDREN – DO NOT TAKE INTERNALLY.