



BEHR PREMIUM® Textured Low-Lustre Enamel Anti-Slip Porch & Patio Floor Paint

- Interior/Exterior Textured Slip Resistant Paint Finish
- Mildew Resistant Finish
- 100% Acrylic Latex
- Available in Custom Colors
- Resists Cracking & Peeling
- Withstands Scuffing & Fading

No. 6250 Ultra Pure White®
No. 6230 Deep Base
No. 6294 Silver Gray
No. 6295 Slate Gray



Spread Rate:
Rough 75-125 Sq. Ft.
Smooth 100-150 Sq. Ft.



Dry Time:
2 Hr. Dry to Touch.
2-4 Hr. Recoat



Clean-Up:
Soap & Water



Protect
from Freezing

CAUTION: Painted surfaces may become slippery when wet.

WHERE TO USE

- Ideal for Wood and Concrete Porches, Patios, Pool Decks, Walkways, Steps, Ramps, and Basement Floors. **Do not use on areas subject to automotive tires or hydrostatic pressure.** Meets ADA Guidelines for Slip Resistance of Ground and Floor Surfaces.

PREPARATION† (Proper Surface Preparation is Required.)

- All surfaces must be clean, sound, dry and free of any dirt, oil and grease.
- Remove mildew stains with a mildew stain removing product.
- **New or Weathered Wood:** Use a product such as BEHR PREMIUM® No. 63 All-In-One Wood Cleaner. Lightly sand to remove remaining wood fibers/fuzz.
- **Painted Surfaces-Wood:** For a painted surface in sound condition, use a product to clean and prepare the surface. If the coating is failing or peeling, use a paint stripper to remove old coating. Scuff sand glossy surfaces. Use stainless steel or galvanized nails to prevent nail staining. Countersink nail heads, repair imperfections and sand smooth. Remove all dust with a damp cloth, allow to dry.
- **Uncoated Concrete or Masonry Surfaces:** Allow new surfaces to cure 30 days. Clean and etch surface using a product such as a muriatic acid etcher (read and follow all manufacturer's label directions) to achieve a textured profile similar to 150 grit sandpaper. Wipe your fingers over the clean, dry floor to check for dust or powder. Ensure there is no residue on your fingers that may have been left from the etcher. If residue is found, rinse the surface to remove residue. Allow the surface to dry completely. Sprinkle a few drops of water onto the surface. If water is quickly absorbed and the surface feels like 150 grit sandpaper, the surface is ready. If not, re-etch.
- **Painted Surfaces-Concrete:** For a painted surface in sound condition, use a product to clean and prepare the surface. If the coating is failing or peeling, use a paint stripper to remove old coating or scrape/sand down to a sound concrete surface. Scuff sand glossy surfaces. Clean and spot etch any exposed concrete. Remove all dust with a damp cloth, allow to dry.

PRIME

- **Interior/Exterior Wood:** Over uncoated and previously coated surfaces, use a product such as BEHR PREMIUM® No. 436 Multi-Surface Primer & Sealer.
- **Interior/Exterior Concrete or Masonry:** Over uncoated surfaces, use a product such as BEHR PREMIUM® No. 880 Concrete & Masonry Bonding Primer.

APPLICATION

- Use product when the surface and air temperatures are between 50-90° F (10-32° C).
- Stir paint occasionally.
- When working with more than one can of the same product, intermix to ensure color uniformity.
- Use a high quality 3/8" nap roller, nylon/polyester brush or a textured sprayer capable of 1.0 GPM with a 3 mm tip.
- For smooth surfaces, use 1/4" nap roller.
- Do not use with airless sprayer.
- Spread rate varies, depending on the surface texture, porosity and application method.
- Two coats are required for optimal coverage, hide, and durability.
- Do not thin if using a roller or brush; however, if using a sprayer and thinning is required, thin with water at a rate of no more than 1/2 pint per gallon.

DRY TIME

- Longer dry time required in cooler temperatures and in higher humidity. Allow 72 hours before subjecting to normal use. After 30 days, cured paint film may be cleaned with a mild, non-abrasive liquid detergent. Dry paint film is mildew resistant.

DISPOSAL

- Properly dispose of all soiled rags. For disposal of empty containers and unused product, contact your household refuse collection service.

LIMITED WARRANTY

- Visit behr.com/warranty or call 1-800-854-0133 for more information.

† **WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. Contact the National Lead Information Center at 1-800-424-LEAD or log on to www.epa.gov/lead

⚠ WARNING: This product can expose you to chemicals including ethylene oxide, which is known to the State of California to cause cancer and birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.

WARNING! CAUSES EYE AND SKIN IRRITATION. MAY CAUSE RESPIRATORY TRACT IRRITATION. CONTAINS CARBON BLACK, CRYSTALLINE SILICA, AND TITANIUM DIOXIDE. Avoid contact with skin and eyes and avoid breathing vapors, spray mist and sanding dust. Sanding, grinding or abrading may release sanding dust, which may be harmful if inhaled and has been shown to cause lung damage or cancer with long term exposure. Do not breathe dusts, vapor, or spray mist. To avoid breathing in dust, vapors, and spray mist, open windows and doors or use other means to ensure fresh air entry during application, drying, sanding, and/or abrading. If properly used, a respirator (NIOSH approved with particulate pre-filter) may offer additional protection and should be used if adequate ventilation cannot be provided; obtain professional advice before using. If you experience eye watering, headaches, or dizziness during application or drying, increase fresh air or leave the area. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use. **FIRST AID:** If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 20 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

KEEP OUT OF REACH OF CHILDREN – DO NOT TAKE INTERNALLY.



©2024 Behr Process LLC
Santa Ana, CA 92705 U.S.A. • behr.com
VOC <50 g/L • REV. 10/24