

## Technical information sheet

### Solventum™ Medical Silicone Tape 2477P

#### Product description

Medical Silicone Tape 2477P is double-sided and consists of proprietary silicone adhesive designed for general taping to sensitive or fragile skin, a conformable TPE film carrier, and a pressure sensitive acrylate adhesive. May be used for health care medical devices.

#### Features and benefits

- Dual adhesive system
  - Gentle silicone adhesive for attachment to skin, short-term wear, and can be repositioned (after initial application)
  - Acrylate adhesive for bonding to substrates
- Biocompatible and ETO compatible
- Conformable translucent
- Fluid resistant
- Breathable
- Printable liners
- General medical device use

#### Composition

|                            |  |
|----------------------------|--|
| <b>Film release liner</b>  | ~3 mil (76.2 µm) clear polyester, non-silicone/non-fluorinated release coated one side |
| <b>Silicone adhesive</b>   | ~4 mil (101.6 µm) gentle silicone adhesive   |
| <b>Film carrier</b>        | ~1.5 mil (38.1 µm) translucent TPE film  |
| <b>Acrylate adhesive</b>   | ~1.7 mil (43.18 µm) non-tackified acrylate adhesive                                    |
| <b>Paper release liner</b> | ~3.5 mil (88.9 µm) bleached paper, silicone release coated one side                    |

**Wind orientation** – paper release liner out

#### Roll description

|                            |  |
|----------------------------|--|
| <b>Roll length maximum</b> | 220 yds (201 m)  |
| <b>Roll length minimum</b> | 25 yds (22.86 m)   |
| <b>Roll width maximum</b>  | 23.75 in (603 mm)  |
| <b>Roll width minimum</b>  | 1 in (25.4 mm)   |
| <b>Splices per roll</b>    | Maximum 4 per 100 yds (91 m), 6 per 200 yds (183m), 8 per 220 yds (201m) |

## Typical properties

|  |             |                  |              |
|--|-------------|------------------|--------------|
| <b>Adhesion to steel, 180° peel, silicone side</b> | ~0.43 N/cm  | ~110 gmf/2.54 cm | ~3.9 ozf/in  |
| <b>Liner release, 180° peel, silicone side</b>     | ~0.055 N/cm | ~14 gmf/2.54 cm  | ~0.51 ozf/in |
| <b>Adhesion to steel, 180° peel, acrylate side</b> | ~2.3 N/cm   | ~590 gmf/2.54 cm | ~21 ozf/in   |
| <b>Liner release, 180° peel, acrylate side</b>     | ~0.10 N/cm  | ~26 gmf/2.54 cm  | ~0.91 ozf/in |

Test results, length, and width (minimum and maximum) represent a typical value and should not be used for specification purposes.  
1 N = ~102 gmf / ~3.6 ozf, 2.54 cm = ~1 inch.

**Biocompatibility testing:** Product 2477P has been subjected to the following safety evaluations.

| <b>Study type</b> | <b>Test method</b>                        | <b>Standard</b> | <b>Result</b>   |
|-------------------|---|-----------------|-----------------|
| Cytotoxicity      | Agar overlay                              | ISO 10993-5     | Not cytotoxic   |
| Cytotoxicity      | MEM elution                               | ISO 10993-5     | Not cytotoxic   |
| Skin Irritation   | ISO skin irritation study in rabbits      | ISO 10993-10    | Non-irritating  |
| Sensitization     | ISO guinea pig maximization sensitization | ISO 10993-10    | Non-sensitizing |

## Recommended storage conditions & shelf life

Product as supplied by Solventum in original packaging will maintain stated properties for a period of two (2) years from date stamped on shipping container when stored at temperatures of 50-80°F (10-27°C) and a relative humidity between 40-60 percent. Product should be stored in the original packaging out of direct sunlight or high intensity indoor lighting.

Conditions based on Solventum internal studies may not be representative of actual end use/performance and we recommend our OEM customers run their own studies using their device design.

**Product and safety information:** User is solely responsible for determining the suitability of Solventum samples and products for the intended use including any necessary safety or toxicity assessment. Solventum will provide Material Safety Data Sheets or equivalent and summary results of biocompatibility testing upon request. In every case before using any product in full scale production users should conduct their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purposes under their own operating conditions.

**Notice:** Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendations to practice any invention covered by any patent, without authority from the owners of this patent.

#### **Warranty information**

All statements, technical information and recommendations herein are based on tests Solventum believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Solventum warrants only that products will meet Solventum's specifications at the time of shipment to the customer. Solventum does not offer any other warranty and does not warrant the performance, safety or such other characteristics of products in combination with other materials. Solventum specifically **does not** warrant products for any intended or unintended uses (whether or not foreseeable); for compatibility or suitability with other components or compatibility with any methods of manufacture or conversion. The foregoing warranty is made in lieu of all other warranties, expressed or implied, including the implied warranties of merchantability, fitness for a particular purpose and freedom from non-infringement.

**Limitation of remedies:** If products are proven not to meet Solventum's specifications, the sole and exclusive remedy available and Solventum's only obligation shall be, at Solventum's option, to replace such quantity of products which are proven out of specification or to refund the purchase price paid for products.

**Limitations of liabilities:** The remedies provided herein are exclusive remedies against Solventum for any alleged or actual nonconformance to specifications or defect or other failure in products or for Solventum's performance of its supply obligations. Under no circumstances is Solventum liable for any direct, indirect, incidental, special or consequential damages (including lost profits) in any way related to the product under any theory of law including, but not limited to, negligence and strict liability.

#### **Ordering information**

Call us at Customer Service to place an order: 800-742-1994 (U.S.).

Visit our website: [go.Solventum.com/MedTechOEM](https://go.Solventum.com/MedTechOEM) for product and services information, news about conferences we will be attending, new product highlights or to make a direct inquiry.

To have a sales representative contact you, to request samples or clinical and safety summaries, please contact us at Solventum Helpline 800-742-1994 (U.S.) or for international inquiries, please contact your local country representative.



**Solventum MedTech OEM**

**Phone** 1-800-742-1994

**Web** [go.Solventum.com/MedTechOEM](https://go.Solventum.com/MedTechOEM)

©Solventum 2026. Solventum, the S logo and other trademarks are trademarks of Solventum or its affiliates.

792135