

3M™ Capillary Membrane MF-PP Series, Type S6/2

Chemical Composition	
Polymer	Polypropylene
Residual oil content	≤ 100 ppm
Wetting property	Hydrophobic

Physical Properties	
Wall thickness	450 ± 50 µm (17.7 ± 2.0 mil)
Inner diameter	1800 ± 150 µm (70.9 ± 5.9 mil)
Burst pressure	≥ 8 bar (≥ 116 psi)
Implosion pressure	≥ 4 bar (≥ 58 psi)

Membrane Performance Characteristics	
Bubble point (in isopropyl alcohol, 23 °C)	≥ 0.95 bar (≥ 13.8 psi)
Transmembrane flow (isopropyl alcohol, 23 °C)	≥ 2.0 ml/(min cm² bar) (≥ 128.1 ml/(min ft² bar)) (≥ 0.9 ml/(min in² bar))

Available Make-up Configurations	
Bundles (customer specified)	

All specifications are based on 3M internal test procedures.

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

3M and Membrana are trademarks of 3M Company. © 2018 3M Company. All rights reserved.

3M
Separation and Purification
Sciences Division
13840 South Lakes Drive
Charlotte, North Carolina
28273 USA
Phone: +1 704 587 8888
Fax: +1 704 587 8610

3M Deutschland GmbH
Separation and Purification
Sciences Division
Öhder Straße 28
42289 Wuppertal
Germany
Phone: +49 202 6099 - 0
Fax: +49 6099 - 241

IM-1025
Rev. 12/2018

www.3m.com/membrana