



MedTech OEM Segment

## Solventum™ Medical Silicone Tape 2487

### Product Description

Medical Double Coated Tape 2487 consists of proprietary hi-Tack silicone adhesive for gentle skin attachment with a translucent polyurethane film carrier, and pressure sensitive acrylate adhesive. This double coated adhesive allows design engineers to use gentle silicone skin attachment in multi-layer constructions. May be used for healthcare medical devices.

### Features and Benefits

- Dual Adhesive System
  - Gentle Hi-Tack Silicone Adhesive for attachment to Skin, Minimize Skin and Hair Trauma Upon Removal, and can be Repositioned (After its Initial Application)
  - Gentle Silicone Adhesive May be Used for General Taping to Sensitive/Fragile Skin
  - Excellent Skin Adhesion Up to 7 Days (Silicone Side), Acrylate Adhesive for Bonding to Substrates
- Biocompatible
- Flexible, Conformable, and Fluid Resistant
- EtO Sterilization Compatible
- Printable Liner (Silicone Side)
- General Medical Device Use

### Composition

Release Liner (Silicone Side)	~3 mils (~76.2 μm) Clear Polyester Film with Non-Silicone/Non-Fluorinated Release, One Side
Adhesive (Silicone)	~4 mils (~101.6 μm) Hi-Tack Medical Silicone Adhesive
Carrier	~0.9 mils (~22.9 μm) Translucent Polyurethane Film
Adhesive	~1 mil (~25.4 μm) Medical Grade Non-Tackified Acrylate Adhesive
Release Liner (Acrylate Side)	~3 mils (~76.2 μm) Glassine Paper Liner, Silicone Release Coated Both Sides

Wind Orientation – Kraft Paper Liner (Acrylate Side) Out

Roll Description	
Roll Length Maximum	500 yds (457m)
Roll Length Minimum	25 yds (22.9m)
Roll Width Maximum	24 in (609.6 mm)
Roll Width Minimum	1 in (25.4mm)
Splices per Roll	3 Per 100 yards (91m), 5 Per 200 yards (182m), 7 Per 300 yards (274m), 9 Per 400 yards (365m), 11 per 500 yards (457m)

Typical Properties:			
Adhesion to Low density Polyethylene (LDPE), 180° Peel (Silicone Side)	1.09 N/cm	282 gmf/ 2.54cm	9.97 ozf/in
Adhesion to Stainless Steel, 180° Peel (Acrylate Side)	3.38 N/cm	875 gmf/2.54cm	30.9 ozf/in
Liner Release (Silicone Side), 180° Peel	0.02 N/cm	5.18 gmf/2.54cm	0.18 ozf/in
Release from liner (Acrylate Side), 180° Peel	0.17 N/cm	44.1 gmf/2.54cm	1.55 ozf/in

Test results, length, and width (minimum and maximum) represent typical values and should not be used for specification purposes.

1 N = ~102 gmf or ~3.6 ozf, 2.54 cm = ~1 inch.

Adhesion data for an adhesive/backing combination from a specified substrate can be impacted by dwell time, temperature, humidity, peel-angle and peel-speed.

### Biocompatibility Testing

Product 2487 has been subjected to the following safety evaluations.

Study Type	Tested Method	Standard	Results
Cytotoxicity	Agar overlay	ISO 10993-5	Not cytotoxic
Cytotoxicity	MEM Elution	ISO 10993-5	Not cytotoxic
Skin Irritation	ISO Skin Irritation Study in Rabbits	ISO 10993-10	Non-Irritating
Sensitization	ISO Guinea Pig Maximization Sensitization	ISO 10993-10	Non-Sensitizing

### Recommended Storage Conditions & Shelf Life\*

Product as supplied by Solventum in original packaging will maintain stated properties for a period of two (2) years from date stamped on shipping container when stored at temperatures of 50-80°F (10-27°C) and a relative humidity between 40-60 percent. Product should be stored in the original packaging out of direct sunlight or high intensity indoor lighting.

\*Shelf life relates to the Solventum warranty period for product performance compliant with release specification. When the product is converted in any way, the shelf life of the converted part and/or the shelf life of the end device that the product is incorporated into should be established by OEM customers. Storage conditions based on Solventum internal studies; these may not be representative of actual storage conditions for end use/material incorporated in medical device. We recommend our OEM customers run their own studies using their device design and required storage conditions.

**Product and safety information:** User is solely responsible for determining the suitability of Solventum samples and products for the intended use including any necessary safety or toxicity assessment. Solventum will provide Material Safety Data Sheets or equivalent and summary results of biocompatibility testing upon request. In every case before using any product in full scale production users should conduct their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purposes under their own operating conditions.

**Notice:** Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendations to practice any invention covered by any patent, without authority from the owners of this patent.

#### **Warranty information**

All statements, technical information and recommendations herein are based on tests Solventum believes to be reliable, but the accuracy or completeness thereof is not guaranteed. Solventum warrants only that products will meet Solventum’s specifications at the time of shipment to the customer. Solventum does not offer any other warranty and does not warrant the performance, safety or such other characteristics of products in combination with other materials. Solventum specifically **does not** warrant products for any intended or unintended uses (whether or not foreseeable); for compatibility or suitability with other components or compatibility with any methods of manufacture or conversion. The foregoing warranty is made in lieu of all other warranties, expressed or implied, including the implied warranties of merchantability, fitness for a particular purpose and freedom from non-infringement.

**Limitation of remedies:** If products are proven not to meet Solventum’s specifications, the sole and exclusive remedy available and Solventum’s only obligation shall be, at Solventum’s option, to replace such quantity of products which are proven out of specification or to refund the purchase price paid for products.

**Limitations of liabilities:** The remedies provided herein are exclusive remedies against Solventum for any alleged or actual nonconformance to specifications or defect or other failure in products or for Solventum’s performance of its supply obligations. Under no circumstances is Solventum liable for any direct, indirect, incidental, special or consequential damages (including lost profits) in any way related to the product under any theory of law including, but not limited to, negligence and strict liability.

#### **Ordering information**

Call us at Customer Service to place an order: 800-742-1994 (U.S.).

Visit our website: [go.Solventum.com/MedTechOEM](https://www.solventum.com/MedTechOEM) for product and services information, news about conferences we will be attending, new product highlights or to make a direct inquiry.

To have a sales representative contact you, to request samples or clinical and safety summaries, please contact us at Solventum Helpline 800-742-1994 (U.S.) or for international inquiries, please contact your local country representative



**Solventum MedTech OEM**

**Phone** 1-800-742-1994

**Web** [go.Solventum.com/MedTechOEM](https://www.solventum.com/MedTechOEM)

©Solventum 2025. Solventum, the S logo and other trademarks are trademarks of Solventum or its affiliates.

792064